


MIM Ni as Sintered

Material Properties	Kinetics	
	Theoretical	Typical
Electrical Resistivity ohmm	6.8 E-8	9.3 E-8
Sintered Density (g/cm ³)	8.9	8.6



Material Description

Most commonly used for applications requiring:

- Electrical conductivity
- Corrosion resistance